



Atlas®

Product information

Typical applications: Mooring and tension winch mooring.

Generally: A 6 strand construction gives Atlas excellent shape retention and its elastic properties counter the need for mooring springs. Hardwearing monofilaments provide good resistance to surface abrasion. The outer filler yarns of Atlas fur up and form a shield providing excellent resistance to surface abrasion.

Relative density: 1,14.

Melting point: 220°C.

Shrinkage (cold water): Up to 10%.

Water uptake: Up to 10%.

UV resistance: Very good.

Abrasion resistance: Excellent.

Break elongation: Approx 28%.

Rope construction: 6 strand with core.

Material: Nylon multifilament yarn and nylon monofilaments.

Marking: None

Finish: Natural (white).

Part Code	Diameter mm	MBL	Length m	Circ. inches	Weight kg/220m	Delivery time
300604002200030	40	31	220	5	220	10
300604402200030	44	42	220	5,5	275	10
300604802200030	48	50	220	6	326	10
300605202200030	52	54	220	6,5	361	10
300605602200030	56	67	220	7	440	10
300606002200030	60	70	220	7,5	475.5	10
300606202200030	62	79	220	7,75	517	10
300606402200030	64	81	220	8	539	10
300606802200030	68	94	220	8,5	616	10
300607002200030	70	103	220	8,75	682	10
300607802200030	78	120	220	9,75	801	10
300608402200030	84	140	220	10,5	935	10
300609002200030	90	165	220	11,25	1,111	10
300609602200030	96	190	220	12	1,287	10